

**CERTIFICATE OF ANALYSIS**

**CERTIFICATE NO.** 1034323.1A

**CUSTOMER**

Domus S.A  
 208-210 Thivon Str.  
 GR-182 33 Agios Ioanis Renti  
 Greece

**CUSTOMER REF.**

**SAMPLE DETAILS**

Domus Painted Handles

**DATE RECEIVED** 11-Dec-17

**METHOD: (Determination of Antibacterial Activity using Modified ISO 22196)**

**DATE ANALYSED** 13-Dec-17

**DATE REPORTED** 20-Dec-17

**RESULTS (AS CFU CM -2)**

SAMPLE		CONTACT TIME		LOG REDUCTION	% DIFFERENCE
		0	24		
Polypropylene	<i>E. coli</i>	1.1E+04	8.0E+05	-	-
Domus Handles Euro 6210 Special Treatment	<i>E. coli</i>	1.1E+04	≤ 5.0	≥ 3.4	≥ 99.96%
Polypropylene	<i>S aureus</i>	1.6E+04	2.4E+04		-
Domus Handles Euro 6210 Special Treatment	<i>S aureus</i>	1.6E+04	≤ 5.0	≥ 3.5	≥ 99.97%

The above data shows the difference in the population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95% relative to the initial population.

NS = Poor survival on control supplied.

INDUSTRIAL MICROBIOLOGICAL SERVICE LTD  
 PALE LANE  
 HARTLEY WINTNEY  
 HANTS  
 RG27 8DH  
 UK

RICHARD WEBB  
 LABORATORY MANAGER

